

# Technische Kunden-Information

ISO-9001/14001-zertifiziert

## Glanzgrade der wichtigsten Baumalerprodukte

Produkt	∠ Messwinkel	Messwert %
AlgiBloc	85°	3
Alligator Aussenvorlack 7500	85°	30
BO-Innendispersion	85°	8.5
Boscapox Aqua-2K-Emaille 4000	60°	78
EmulSan	85°	1.5
Expoflex Fassadenmattfarbe	85°	2.2
Exponal Mega	85°	3.8
Exponit ***	85°	3
Exponit 2000	85°	2.5
Exponit BB	85°	3.3
Exponit Protect	85°	0.6
Exponit PU-Latex 20	85°	20
Exponit PU-Latex 40	85°	35
Exponit PU-Latex 5	85°	4
ExpoSan Clima	85°	1.5
ExpoSil Siliconharzfarbe	85°	2
ExpoSilit Interior	85°	1.5
ExpoSol Cristal	85°	1.5
ExpoSol Wohnraumfarbe	85°	1.3
HydroSil	85°	3
KaliPhil	85°	0.8
KaliSan	85°	2.5
Kasein Tempera	85°	9
Leimfarbe klassisch	85°	10
Lithomatt L	60°	2
MicroSil Ultra	85°	1.25
Ökofix Leimfarbe	85°	8
ÖkoSan	85°	1.1
ÖkoSil	85°	3.5
PigaPur Exterior	60°	60
PigaPur Finish DS	60°	30
PigaPur Flex	60°	30
PigaPur Interior 20	60°	20
PigaSil 50 Venti	60°	50
PigaSil 70 glanz	20°	85
ReboFlex Finish seidenmatt	85°	4
Samuro antico	85°	1
Samuro	85°	4
Saxolit	85°	1.9
Saxotol Decklack glanz	60°	88
Saxotol Decklack seidenglanz	60°	58

Saxotol Klarlack seidenglanz	60°	30
Solikat	85°	3
ThermoSil	85°	2